BR-193

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.18/BRM/CSR-06/865g/CEMENT/2015-16 Date: 02.06.2015

TEST REPORT ON CEMENT

* CUSTOMER	:	**Asst. Executive Engineer**, J.C. Nagara Sub Division, BBMP, Bangalore.
*AGENCY	:	**Mr. B.R. Manjunath,** No. 486, New BEL Road, Bangalore - 54.
*NAME OF THE WORK	:	Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.
*REFERENCE	:	EE/H/AE/WO/191/2012-13 Dated: 07.11.2012
SAMPLE ID	:	Cement
SAMPLE RECEIVED ON	:	01.06.2015
PERIOD OF TESTING	:	01.06.2015 to 02.06.2015

The results of the tests conducted on the cement sample are as follows:

Sl. No	Descriptions	Test Method as per IS	Test Result	Requirements as per IS: 8112-2013
1	Standard Consistency	IS-4031 (Part -4) 1988(RA-2009)	28.00 %	-
2	a) Initial Setting Time	IS-4031 (Part -5) 1988(RA-2009)	150 Minutes	Not Less than 30 Minutes
	b) Final Setting Time	IS-4031 (Part -5) 1988(RA-2009)	470 Minutes	Not More than 600 Minutes
3	Soundness by Le Chartlier Method	IS-4031 (Part-3) 1988(RA-2009)	1 mm	Not more than 10mm

*Information is furnished by the Customer/Representative.

Note:

⇒ The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒ The results indicated above are based on the tests carried out on the samples received in the laboratory.

⇒ Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

No: CTCE/BBMP/W.No.18/BRM/CSR-06/865g/SAND-Gradation/2015-16 : 02.06.2015

TEST REPORT ON DETERMINATION GRADATION OF FINE AGGREGATES

*** Customer** : **Asst. Executive Engineer,** J.C. Nagara Sub Division, BBMP, Bangalore.

*** Agency** : **Mr. B.R. Manjunath,**
No. 486, New BEL Road, Bangalore - 54.

*** Name of Work** : Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.

Reference : EE/H/AE/WO/191/2012-13 Dated: 07.11.2012

Technical Reference : IS : 2386 Part 1 - 1963 RA-2007

Sample ID : Fine Aggregates

Sample Received on : 01.06.2015

Date of Testing : 02.06.2015

Total Wt. of Aggregates in gms **1000**

Is Sieve Size in mm	Cumulative Weight Passing in %	Specific Limits as per IS 383-1970 (RA- 2007)			
		Zone-I	Zone-II	Zone-III	Zone-IV
10	100	100	100	100	100
4.75	95.50	90-100	90-100	90-100	95-100
2.36	75.80	60-95	75-100	85-100	95-100
1.18	52.00	30-70	55-90	75-100	90-100
600 Micron	23.60	15-34	35-59	60-79	80-100
300 Micron	11.50	5-20	8-30	12-40	15-50
150 Micron	2.90	0-10	0-10	0-10	0-15

* Information is furnished by the Customer/Representative

Remarks : This sample is under Zone-I specific limits.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2977

C.T.C.E. BBMP/W.No.18/BRM/CSR-06/865g/AGG/GR/2015-16 : 02.06.2015

TEST REPORT ON DETERMINATION GRADATION OF COARSE AGGREGATES

*** Customer**	: **Asst. Executive Engineer,** J.C. Nagara Sub Division, BBMP, Bangalore.
*** Agency**	: **Mr. B.R. Manjunath,** No. 486, New BEL Road, Bangalore - 54.
*** Name of Work**	: Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.
Reference	: EE/H/AE/WO/191/2012-13 Dated: 07.11.2012
Technical Reference	: IS : 2386 Part 1 -1963 RA-2007
Sample ID	: Coarse Aggregates (40mm)
Sample Received on	: 01.06.2015
Date of Testing	: 02.06.2015

Total Wt. of Aggregates in gms= **5000**

Is Sieve Size in mm	Cumulative Weight Passing in %	Specific Limits as per IS 383-1970 (RA- 2007)	
		Graded	Single Sized
80	100	100	-
63	100	-	100
40	97.26	95-100	85-100
20	33.54	30-70	0-20
10	14.38	10-35	0-5
4.75	1.34	0-5	-

* Information is furnished by the Customer/Representative

Remarks : This sample is under Graded specific limits.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.18/BRM/CSR-06/865g/AGG/GR/2015-16 : 02.06.2015

TEST REPORT ON DETERMINATION GRADATION OF COARSE AGGREGATES

*** Customer** : **Asst. Executive Engineer,** J.C. Nagara Sub Division, BBMP, Bangalore.

*** Agency** : **Mr. B.R. Manjunath,**
No. 486, New BEL Road, Bangalore - 54.

*** Name of Work** : Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.

*** Reference** : EE/H/AE/WO/191/2012-13 Dated: 07.11.2012

Technical Reference : IS : 2386 Part 1 -1963 RA-2007

Sample ID : Coarse Aggregates (20mm)

Sample Received on : 01.06.2015

Date of Testing : 02.06.2015

Total Wt. of Aggregates in gms= **5000**

Is Sieve Size in mm	Cumulative Weight Passing in %	Specific Limits as per IS :383-1970 (RA- 2007)	
		Graded	Single Sized
40	100	100	100
20	97.44	95-100	85-100
10	30.96	25-55	0-20
4.75	2.84	0-10	0-5

* Information is furnished by the Customer/Representative

Remarks : This sample is under Graded specific limits

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laborator
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.18/BRM/CSR-06/865g/Bricks/2015-16 : 05.06.2015

TEST REPORT ON BRICKS

*** Customer** : **Asst. Executive Engineer,** J.C. Nagara Sub Division, BBMP, Bangalore.

*** Agency** : **Mr. B.R. Manjunath,**
No. 486, New BEL Road, Bangalore - 54.

*** Name of the work** : Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.

Reference : EE/H/AE/WO/191/2012-13 Dated: 07.11.2012

Sample ID/Type of Test : Bricks / Water Absorption of Bricks

Technical Reference : IS: 3495(Part-2)- 1992 (RA-2007)

Sample Received on : 01.06.2015

Date of Testing : 05.06.2015

Sl.No.	Size of Bricks in mm	Dry weight in gms	Wet weight in gms	Water Abosorption in %	Average Water Absorption in %	Allowable Water absorbtion as per IS: 1077:1992 Clause 7.2)
1	220x100x75	2945	3286	11.58	11.50	Not exceeding 20%
2	220x100x75	2953	3289	11.38		
3	220x100x75	2946	3283	11.44		
4	220x100x75	2938	3285	11.81		
5	220x100x75	2962	3296	11.28		

* Information is furnished by the Customer/Representative

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.18/BRM/CSR-06/865g/Bricks/2015-16 : 05.06.2015

TEST REPORT ON BRICKS

*** Customer** : **Asst. Executive Engineer,** J.C. Nagara Sub Division, BBMP, Bangalore.

*** Agency** : **Mr. B.R. Manjunath,**
No. 486, New BEL Road, Bangalore - 54.

*** Name of the work** : Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.

Reference : EE/H/AE/WO/191/2012-13 Dated: 07.11.2012

Sample ID/Type of test : Bricks / Compressive Strength of Bricks

Technical Reference : IS: 3495(Part-1)- 1992 (RA-2007)

Sample Received on : 01.06.2015

Date of Testing : 05.06.2015

Sl.No.	Size of Bricks are in mm	Weight of Bricks in gms	Failure load in KN	Compressive Strength (N/mm^2)	Average Compressive Strength (N/mm^2)	Class Designation (As per IS: 1077:1992 Table 1)
1	220x100x75	3433.00	120.3	5.47	5.45	5.0
2	220x100x75	3435.00	118.3	5.38		
3	220x100x75	3493.00	119.5	5.43		
4	220x100x75	3502.00	120.3	5.47		
5	220x100x75	3493.00	121.5	5.52		

* Information is furnished by the Customer/Representative

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory
An ISO 9001:2008 Certified Company
NABL - Accredited Laboratory as per ISO / IEC-17025 : 2005

Job No.: CTCE/BBMP/W.No.18/BRM/GSWPipe/2015-16

08.06.2015

TEST REPORT ON GLAZED STONEWARE PIPE

* Customer	:	Asst. Executive Engineer, J.C. Nagara Sub Division, BBMP, Bangalore.
* Agency	:	Mr. B.R. Manjunath, No. 486, New BEL Road, Bangalore - 54.
* Name of work	:	Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.
* Reference	:	EE/H/AE/WO/191/2012-13 Dated: 07.11.2012
* Sample ID	:	Glazed Stoneware Pipe(150mm dia)SP-1 Class
Techinical Reference	:	IS-651:2007 (VI revision)
Date of Testing	:	08.06.2015

Sl no	Internal Diameter	Thickness of Pipe	% absorption	% of Acid Resistance	Crushing Strength kN/m
1	150mm	15mm	4.8	1.72	17.15
2	150mm	15mm	5.2	1.89	18.50
3	150mm	15mm	5.4	1.95	17.95
Requirements as per IS-651:2007(VI Revision)	-----	----	**Maximum 6%**	**Not Exceed 2.5%**	**Minimum 16kN/m**

*Information is furnished by the Customer/Representative.

Note:

- ⇒The report shall not be reproduced, except in full, without the written approval of the laboratory.
- ⇒The results indicated above are based on the tests carried out on the samples received in the laboratory.
- ⇒Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.K.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.18/BRM/CSR-06/865g/CUBE/2015-16 20.07.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*** Customer** : **Asst. Executive Engineer,** J.C. Nagara Sub Division, BBMP, Bangalore.

*** Agency** : **Mr. B.R. Manjunath,**
No. 486, New BEL Road, Bangalore - 54.

*** Name of the work** : Providing sanitary connection to the Public Toilet at Bulleward Park in Ward No. 18, BBMP, Bangalore.

*** Reference** : EE/H/AE/WO/191/2012-13 Dated: 07.11.2012

*** Sample ID** : Cement Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

*** Grade of Concrete** : M_{15}

Compressive Strength as on : 28th day

Sample Received on : 20.07.2015

Sl.No.	* Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	22.06.2015	20.07.2015	8.132	365.7	16.25
2	22.06.2015	20.07.2015	8.295	378.6	16.83
3	22.06.2015	20.07.2015	8.338	389.4	17.31

* Information is furnished by the Customer/Representative

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VIDYARANI P.L.
Technical Manager

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com